



- The flooring shall be Polysafe Hydro, as manufactured by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC sheet flooring in 2.0mm thickness, containing silicon carbide, coloured quartz and aluminium oxide granules, to impart enhanced slip resistance.
- The flooring shall be manufactured by spreading liquid PVC onto a bonded scrim-tissue in one operation. The bonded scrim-tissue shall be fully encapsulated in PVC.



- The flooring material shall fully conform with the European Norm for safety flooring - EN 13845.
- In respect of flamespread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class Bfl-S1, achieving the criteria EN ISO 9239-1 $\geq 8 \text{kw/m}^2$ and the mandatory requirement of EN ISO 11925-2 Pass. It shall have been fully tested to ASTM E648 by an independent test house and have a Class 1 rating, making it suitable for use in institutional, commercial and public buildings.
- The flooring must have been fully tested by an independent test house to meet the requirement of EN 13845 Barefoot and on the RRL Pendulum Test (4S & TRL Rubber) have results of ≥ 36 in the wet, with a surface roughness of $R_z \geq 20 \mu\text{m}$. A result of Class B to AS/NZS 4586 Part C should be achieved.
- The product must have been fully tested for abrasion resistance to the Frick Taber test EN 660: part 2 and be in abrasion group P, as defined in EN 649.
- This product does not accumulate static charges above 2kV and is classified as 'antistatic' when tested to EN 1815. For specialist applications where there is a requirement to dissipate the electrostatic charge, see the Polyflor ESD product ranges.
- The flooring shall possess a valid Agrément certificate rating the product G5ws, when laid in accordance with the instructions of Polyflor, with coved skirtings and welded joints.
- The flooring must be available in 2.0 metre width, to minimise the number of joints.
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 and obtain ≥ 6 .



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001: 2000.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed, as outlined by Polyflor.
- Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
- All joints must be welded.



- Polysafe Hydro is specially designed with a raised profile emboss, giving greater confidence in specifying for areas that are subjected to constant running water and where enhanced slip resistance is a prime consideration. Suitable for areas where barefoot or soft soled footwear is worn - examples include walk-in showers, hydrotherapy areas and barefoot recreational areas such as changing room facilities and indoor swimming pool surrounds.
- The slip resistance across all Polysafe products is assured throughout the guaranteed life of the product, with strict adherence to HSE Guidelines. As with all Polysafe products, Polysafe Hydro should not have a polish applied. For further information and advice on specific applications, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.



- At the date of issue the data presented is correct. However, Polyflor Ltd. reserves the right to make changes which do not adversely affect performance or quality.

POLYFLOR

POLYSAFE™ HYDRO

SAFETY FLOORING

PRODUCT SPECIFICATION

POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK
 TEL: +44 (0)161 767 1111 UK SALES DIRECT: +44 (0)161 767 1122 UK FAX: +44 (0)161 767 1128
 EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM WWW.POLYFLOR.COM
 UK SAMPLE REQUESTS: +44 (0)161 767 2551

James Hulstead
FLOORING



POLYFLOR™
COVERING THE WORLD